



Propriétés de nos aciers

	Carbone	Chrome	Molybden	Tungstene	Cobalt	Valadium	Dureté
M35	0.93	4.20	5.00	6.40	4.80	1.80	64/66 HRC
M42	1.08	3.80	9.40	1.50	8.00	1.20	65.5/67 HRC
10%	1.27	4.00	3.60	9.50	10.00	3.20	66/67.5 HRC
ASP60	2.30	4.20	7.00	6.50	10.50	6.50	67/68.5 HRC
ASP30	1.28	4.20	5.00	6.40	8.50	3.10	65/66 HRC