



Vitesses de rotation indicatives pour forets creux HSS-PRO-TIALN

Matière	Ø12-18	Ø19-25	Ø26-32	Ø33-39	Ø40-46	Ø47-50
Acier<750N	350-530	250-340	200-245	165-195	140-160	120-135
Acier<1200N	175-265	130-165	100-125	80-95	70-79	60-67
Acier<1400N	125-185	90-117	70-85	57-67	48-55	42-47